



Your notice of
12-05-2021

Your reference

Date
28-05-2021

Analysis Report 21.03110.01

Required tests :

CFR 1630-FF 1-70

Standard for the surface flammability of carpets and rugs.

Sample id	Information given by the client	Date of receipt
T2110996	Lustrous	12-05-2021



Kristina De Temmerman
Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.
The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.
In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.



Reference: T2110996 - Lustrous

Standard for the surface flammability of carpets and rugs.

Date of ending the test 26-05-2021
Standard used CFR 1630-FF 1-70 & 1631-FF 2-70

Deviation from the standard -

Conditioning 2 hours in a drying oven at 105 °C. After drying cooled to room temperature in a desiccator.

The specimens have been taken from the material as supplied

No cleaning procedure has been applied prior to testing.

Specimens have been tested loose laid on a standard non-combustible substrate.

	Flame time or time to reach the edge	Max. damage from centre point of specimen (mm).	Charred area $\leq$ 25 mm from inside edge.
#1	1 min 48 s	11	no
#2	1 min 32 s	17	no
#3	1 min 54 s	16	no
#4	1 min 23 s	22	no
#5	1 min 46 s	14	no
#6	1 min 35 s	19	no
#7	1 min 48 s	30	no
#8	2 min 00 s	16	no

Test criterion

A specimen fails the test if the charred area reaches a distance of 25 mm or less, from the inside edge of the template.

Acceptance criterion

At least seven of the eight specimens shall meet the test criterion in order to conform with the standard.

Conclusion

Pass